

# H64310 | ULTRA Satin 190

MICROPOROUS RESIN-COATED PAPER

## PRODUCT SPECIFICATION \*

|                                       |                  |      |       |
|---------------------------------------|------------------|------|-------|
| Weight DIN EN ISO 536                 | g/m <sup>2</sup> | 197  | ± 6   |
| Thickness DIN EN ISO 534              | µm               | 203  | ± 6   |
|                                       | mil              | 8.0  | ± 0.2 |
| Gloss BYK (60°) ISO 2813              |                  | 19   | ± 5   |
| Colour Elrepho UVO (D65) ISO 2469     | L                | 94,7 | ± 0,8 |
|                                       | a                | -0,2 | ± 0,5 |
|                                       | b                | -2,6 | ± 0,8 |
|                                       | delta b          | <0,7 | ± 0,8 |
| CIE whiteness (D65/10°) min. ISO 2469 |                  | > 94 |       |
| Opacity min. ISO 2469                 | %                | > 92 |       |

### Printability

Simplex printable

### Laminatability

Hot & cold

### Printing Technology

• Inkjet water-based

### Compatibility

Can be used on all commercial thermal, piezo water-based printing systems like Epson, Canon, Hewlett-Packard, Kodak, Encad etc.

## BENEFITS & PROPERTIES

- Pin-sharp details
- Vivid colours
- High colour consistency and gamut
- High opacity
- High light fastness
- Water resistance
- Outstanding lay-flat performance

## KEY APPLICATIONS

### Wall Decoration

- Posters
- Large-format photo prints

### Sign & Display Graphics

- POS signage
- Exhibition graphics
- Photo prints
- Commercial posters for indoor and short-term outdoor applications

### Directions for use

Store material only in original packaging under normal climatic conditions (23°C, 50 % RH). Protect material from direct sunlight. It is recommended to adapt the material to indoor climate at least 24 hours before usage.

\* Modifications reserved.

Version 02/2016